

# Application information

Protocol No. 6756

**Sample name:** tungsten carbide insert  
**Industry:** tool industry  
**Process required:** rounding of edges  
**Material:** Carbide  
**Manufacturing process:** sintered part

Machine	Stp.	Time	Process	Media	Compound	Speed
DF-3/4 To	1	12 Min.	dry grinding	QZ 1-3 microfinish media	HL 6 oil	30

