

Application information

Protocol No. 6905

Sample name: tungsten carbide insert



Industry: tool industry

Process required: rounding of edges


Material: Carbide

Manufacturing process: grinded parts

Machine	Stp.	Time	Process	Media	Compound	Speed
DF-3/4 To	1	8 Min.	dry polishing	SIX/H050 Mikrofinish granule	HL 6 oil	25



unbearbeitet



bearbeitet

