

Application information



Protocol No. 6744

Sample name: writing instruments
Industry: Metall industry
Process required: polishing
Material: Aluminium
Manufacturing process: turned and machined part

| Machine | Stp. | Time | Process | Media | Compound | Speed |
|---------|------|---------|---------------|-----------------------------|---------------------|-------|
| CF 3x18 | 1 | 2 Std. | dry polishing | H1/100 walnut-shell granule | P 1 polishing paste | 250 |
| CF 3x18 | 2 | 30 min. | dry polishing | H1/400 walnut-shell granule | P 1 polishing paste | 250 |



Before
after

