

# Dealer Information



No.: 0

**Sample name:** turned and machined parts  
**Industry:** Metall industry  
**Process required:** grinding and polishing  
**Material:** Brass  
**Manufacturing process:** Dreh- und Frästeil

Machine	Stp.	Time	Process	Media	Compound	Speed
CF 3x18	1	2,5 h	wet grinding	DZP 6/6 SK porcelain polishing	SP 62 grinding paste	240



Remarks: Compound im Test: SC 12

Description of the sample:	typical turned parts
Process required:	deburring, polishing
Benefits for the customer (regarding quality and function):	debured work piece, polished-looks higher quality
Current method:	by hand
What is the advantage of the OTEC-process in comparison to the customer's current process?	
Recommended machines:	CF 18 wet